

**Product Description**

Vibra-TITE 373 is a single component medium to high viscosity cyanoacrylate adhesive. Suitable for general-purpose bonding but provides excellent strength and speed on all rubber compounds.

**Physical Properties**

**Monomer (Liquid)**

Base Compound	Ethyl Cyanoacrylate
Appearance	Colorless Liquid
Viscosity (cP @ 68°F)	1800 cPs
Specific Gravity (g/cc)	1.06
Flash Point (TCC)	185°F
Shelf Life @40°F	1 year unopened

**Military Specifications**

Mil-A-46050C  
Type II, Class 3

**Curing Properties**

Ambient surface moisture will initiate the hardening process. Handling strength is reached in a short period of time and varies depending on environmental conditions and substrates being bonded. Product will continue to cure for at least 24 hours before full strength and resistances are developed.

**Setting Time (68°F, 65% R.H.)**

Steel	60 seconds
ABS	6 seconds
EPDM	3 seconds
Wood	> 60 seconds

**Curing Performance**

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

**Polymer (Cured)**

Appearance	Colorless Solid
Service Temperature Range	-65°F to 200°F
Softening Point	329°F
Refractive Index (ND 20)	1.49
Full Cure Time	24 Hours
Dielectric Strength (KV/mm)	11.6
Dielectric Constant (@ 1Kc)	5.4
COE (in./in./F)	.000126
Tensile Strength (steel/steel)	3400 psi
Solubility	Nitromethane, Acetone, Dimethylformamide


**Performance of Cured Materials**

Tensile Shear strength after 48 hours at 20° to 25°C

<b>Substrate</b>	<b>Range in N/mm<sup>2</sup></b>
Blasted Steel	19 to 25
Etched Aluminum	12 to 20
Neoprene	> 10
ABS	> 6
Polycarbonate	> 5
PVC	> 6

**Temperature Resistance**

Sheer Strength on steel after 1 week at 22 °C





Cyanoacrylate  
373  
Product Data Sheet

**Chemical Resistance**

Sheer strength on steel after 12 month soak

**% Strength Retained**

*Solvent*

Motor Oil	90
Gasoline	100
Trichloroethane	100
Freon TA	100
10% NaOH	0
10% Hcl	0
Water	0

**General Instructions**

Surfaces to be bonded should be clean and dry.

Dispense a drop or drops to one surface only. Apply only enough to leave a thin film layer after compression.

Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less that one minute and maximum strength is attained in 24 hours.

Wipe off excess adhesive from the top of the container and recap. Cyanoacrylate products if left uncapped may deteriorate by contamination from moisture in the air.

Because Cyanoacrylate products cure by polymerization, whitening may appear on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with acetone.

**For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS)**

**General Information**

**Storage**

Refrigeration at 40 °F provides optimum storage stability.

**Note**

Prior to use, remove all surface contaminants such as oil or grease. Products like isopropyl alcohol can be used. Test compatibility of cleaner with substrate.

Make sure surface is completely dry before bonding.

**Health & Safety in use**

CAUTION: SuperGlues bond skin and eyes on contact. If accidental skin bonding occurs, wash area with warm soapy water and slowly pry skin apart using a blunt object (such as a teaspoon handle.) In case of eye contact, bathe immediately with water and seek immediate medical attention.