

Product Description

Vibra-Tite 642 Cyanoacrylate Remover is a solvent designed to remove cured cyanoacrylate from surfaces. Vibra-Tite 642 can be used to de-bond parts assembled with cyanoacrylates.

Typical Applications

- Cleaning spilled cyanoacrylate off a wide variety of surfaces.
- Removing blooming from parts.

Properties of Uncured Material

Technology	Solvent cleaner
Chemical Type	Nitromethane / hydrocarbon
Appearance	Clear to yellow
Viscosity	Very low
Cure	Not applicable
Application	Removal of cured cyanoacrylate

Procedure for Application

1. Product is normally hand applied from the bottle by brushing, wiping or spraying onto parts.
2. Apply Vibra-Tite 642 to cured cyanoacrylate and allow to set until superglue is softened (Typically 2 to 10 minutes). The length of time for cyanoacrylate removal will depend on the thickness of the cyanoacrylate required to be removed.
3. Thin layers of cyanoacrylates may be removed with a Vibra-Tite 642 soaked cloth.
4. Bonded parts may require several hours of soaking to soften the cyanoacrylate.

Technical Features

Specific Gravity @ 25°C	1.1
Viscosity (cPs)	1.5
Shelf Life @ 68°F (years)	2
Flammability	Yes, High

General Information

Storage

Storage: Keep products in the unopened container in a cool and dry location. Ideal storage temperature is between 2°C and 8°C. Temperatures below 2°C can adversely affect product properties. Do Not Freeze. Keep container tightly closed until ready for use. The Shelf-life is 2 years from date of manufacture.

Note

Handling: Material removed from containers may be contaminated during use. Do not pour back any product to the original container. Misuse of product will void all warranties.

Health & Safety in use

Use in a well-ventilated area and read SDS.