



Product Description

Epoxy *VIBRA*-TITE 917 is a low viscosity, industrial grade epoxy Adhesive and Laminating Resin. Once mixed, the two part epoxy cures at room temperature but optimal physical properties occur when cured between 150 -200°F in a heated compression mold press. When fully cured, the epoxy withstands exposure to a wide range of chemicals and solvents, and has excellent dimensional stability over a wide temperature range.

Features and Benefits

- Easy mix Ratio
- Excellent chemical resistance
- Good impact resistance
- Low shrinkage
- Casting can survive harsh chemical exposure

Properties of Uncured Material (resin)

| Chemical Type Appearance | Epoxy clear/yellow |
|----------------------------------|-----------------------|
| liquid Specific Gravity 1.139 | , |
| Toxicity | Low |
| Solids | 100% |
| Viscosity @ 25°C, cP | 12,000 |
| Flash Point (TCC), °C (°F) | >93(>200) |

Properties of Uncured Material (hardener)

| Chemical Type | Amine |
|---------------------------|--------------------|
| Appearance | Pale yellow liquid |
| Specific Gravity | 1.015 |
| Toxicity | Low |
| Solids | 100% |
| Viscosity @ 25°C, cP | 460 |
| Flash Point (TCC), °C (°F |) >93(>200) |

Properties of Cured Material

| 5 to 1 |
|----------|
| 100:16 |
| 24 mins |
| 180 min. |
| 80 |
| |

Performance Properties

(Substrates cured or 5 days @ 22°C)

Lap Shear

| Abraded Steel | 3,300 psi |
|----------------------|-----------|
| Acid Etched Aluminum | 4,300 psi |
| Galvanized Steel | 3,500 psi |

General Information

Storage

Product should be stored in cool, dry conditions. *VIBRA*-TITE 917 when un-mixed has a shelf life of 12 months when stored at 25°C. Storage in cool, clean areas is recommended. Usable shelf life may vary depending on method of applications and storage conditions.

Note

The data are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is recommended that the product be tested in the application for which it is to be used.

Technical data contained within this document is intended for reference only For assistance and recommendations on specifications for this product, contact ND Industries info@ndindustries.com